




Endurance DYFORM® 18 & 18PI



Diameter	Approx. nominal length mass	Minimum breaking force (Fmin)		Axial stiffness @20% load	Torque generated @20% load		Metallic cross section
		kN	tonnes		Ordinary	Lang's	
mm	kg/m			MN	N.m	N.m	mm²
16	1.27	216	22.0	14	21	31	143
17	1.44	244	24.8	15	25	37	161
18	1.61	273	27.8	17	29	44	181
19	1.79	304	31.0	19	35	52	201
20	1.99	337	34.4	21	40	61	223
21	2.19	372	37.9	23	47	70	246
22	2.41	408	41.6	26	54	81	270
23	2.63	446	45.4	28	62	92	295
24	2.86	485	49.5	31	70	105	321
25	3.11	527	53.7	33	79	119	349
26	3.36	570	58.1	36	89	133	377
27	3.62	614	62.6	39	100	149	407
28	3.90	661	67.4	42	111	167	437
29	4.18	709	72.3	45	123	185	469
30	4.47	759	77.3	48	137	205	502
32	5.09	863	88.0	54	166	249	571

