



BRIDON
SUPERLINE

Nylon OCIMF 2000

Diameter*		Circumference		Approximate mass		MBL new dry		MBL new wet	
				In air					
in	mm	in	mm	kg/m	lb/ft	kN	kips	kN	kips
3 ¹ / ₈	80	10	251.3	4.2	2.8	1462	329	1344	302
3 ⁴ / ₈	88	11	276.5	5.2	3.5	1776	399	1628	366
3 ⁶ / ₈	96	12	301.6	6.1	4.1	2109	474	1942	437
4 ¹ / ₈	104	13	326.7	7.0	4.7	2482	558	2276	511
4 ³ / ₈	112	14	351.9	8.3	5.6	2884	648	2649	595
4 ⁶ / ₈	120	15	377.0	9.5	6.4	3316	745	3041	683
5	128	16	402.1	10.4	7.0	3777	849	3463	778
5 ³ / ₈	136	17	427.3	11.7	7.9	4267	959	3914	880
5 ⁵ / ₈	144	18	452.4	13.2	8.9	4787	1076	4395	988
6	152	19	477.5	14.6	9.8	5337	1199	4905	1102
6 ² / ₈	160	20	502.7	16.2	10.9	5925	1332	5435	1221
6 ⁵ / ₈	168	21	527.8	17.8	12.0	6533	1468	5994	1347
6 ⁷ / ₈	176	22	552.9	19.8	13.3	7181	1614	6592	1482
7 ² / ₈	184	23	578.1	22.2	14.9	7848	1764	7210	1620
7 ⁴ / ₈	192	24	603.2	24.1	16.2	8554	1923	7858	1766
7 ⁷ / ₈	200	25	628.3	26.1	17.5	9290	2088	8525	1916
8 ² / ₈	208	26	653.5	28.6	19.2	10055	2260	9231	2075
8 ⁴ / ₈	216	27	678.6	30.5	20.5	10850	2438	9957	2238
8 ⁷ / ₈	224	28	703.7	32.5	21.8	11674	2624	10722	2410
9 ¹ / ₈	232	29	728.8	35.4	23.8	12537	2818	11507	2586

*Diameters shown in the above table are nominal values and should be used for guidance purposes only.



Figures quoted within published tables represent our standard products.

Bridon specialise in the development of products to suit your individual needs, please contact us directly and we will be pleased to develop a specification to match your requirements.